

PEVALIT Technical Parameters
EGALISATIONSFABRE

Material density: approx. 1.6 g/cm³.

Steam permeability coefficient: Class V1 (high), sd-value: down 0,14 m.

Purpose and Water absorption: Class W3 (low), w-value down 0,1 kg/(m²h^{0,5})

Work temperatures: +5 deg C - +30 deg C.

Spending: approx. 150-200 ml/m². / 200-250 ml/m².

Drying: 12-15 hours based on temp. approx. 20 deg C. and 65% air humidity.

Mixing with water: 5-10%.

Cleaning of tools: After finishing work with water.

Material color: White.

Packaging: 5 l, 15 l.

Best before: In the original packaging 12 months, in a warehouse without moisture.