

PEVALIT Technical Parameters

G5 light

Sanding: From 0-1.5 mm.

Layer thickness: Between 1 cm and 4 cm.

Dry mass density: 1050/1250 kg/m³

Steam permeability coefficient: ca.23.

Norm: MKC EN 998-1/Kop: 2006.

Pressure durability (after 28 days): CS II, ca. 3.2 N/mm².

Purpose and Water absorption: GP, W0.

Work temperatures: +5 deg C - +30 deg C.

Mixing with water: with around 7.2 l/25kg

Material color: Grey.

Packaging: 25 kg.

Best before: In the original packaging 12 months, in a warehouse without moisture.