

PEVALIT Technical Parameters

N BS

Dry mass density: 1830 kg/1m³.

Pressure durability (after 28 days): CS IV, ca. 8.0 N/mm².

Water absorption: W0.

Work temperatures: +5 deg C - +30 deg C.

Working time in container: approximately 30 min after mixing.

Layer thickness: Between 6 and 30 mm.

Mixing with water: with approximately 6.3 l/25kg.

Material color: Grey

Packaging: 25 kg.

Best before: In the original packaging 12 months, in a warehouse without moisture.