

PEVALIT Technical Parameters

P2

Working time in container: Up to 6 hours after mixing.

Working time: Up to 30 minutes.

Work temperatures: +5 deg C - +30 deg C

Resistant to temperatures: -20 deg C - +80 deg C

Norm: C2TE, based on EN 12004.

Walking on tiles: After 24-48 hours. Measurements are based on temp. around 22 deg C.

Walking on tiles with weight: After 4 days.

On layers of plaster: PEVALIT-Tiefgrund LF is used.

Mixing with water: approximately 4 min., with around 24 % water / 25kg.

Packaging: 25 kg.

Material color: Grey.

Best before: In the original packaging 12 months, in a warehouse without moisture.