

PEVALIT G4



Suva çimentoje

APLIKIMI

- Suva me bazë çimentoje.
- Për suvatimin e mureve dhe taveve, në hapësira të jashtme dhe të brendshme.
- Përdorim në fasada, bodrume, banjo, dhoma, etj.
- E adoptueshme për të gjitha llojet e bazamenteve si tulla apo blloqe të pjekura argjili, blloqe betoni apo gëlqeror, etj.
- Hidhet me dorë ose me makinë.
- Para përdorimit në vende nga betoni dhe gas betoni duhet të përdoret lëng lidhës ose ngjitës PEVALIT-G2.

PARAMETRAT TEKNIKË

Layer Thickness	Spending	Surface Covered with 25kg PEVALIT - G4
10 mm	approx. 12kg/m ²	approx. 1.5m ²
15 mm	approx. 18kg/m ²	approx. 1m ²
20 mm	approx. 24kg/m ²	approx. 0.8m ²

- Sanding:** From 0-1.5 mm.
- Layer thickness:** Between 0.8 mm and 4 mm.
- Dry mass density:** 1800 kg/1m³
- Steam permeability coefficient:** ca.23.
- Norm:** MKC EN 998-1/Kop: 2006.
- Pressure durability (after 28 days):** CS II, ca. 3.2 N/mm².
- Purpose and Water absorption:** GP, W₀.
- Temperature conductivity:** □0,75 W/mK.
- Reaction to fire:** A1.
- Work temperatures:** +5°C - +30°C.
- Mixing with water:** with around 7.2 l/25kg
- Material color:** Grey.
- Packaging:** 25 kg.
- Best before:** In the original packaging 12 months, in a warehouse without moisture.