



APPLICATION

One component polyurethane adhesive.

-For thermo insulation polystyrene panel adhesion.

-Surfaces where PEVALIT-PU KLEBER must be used, should be clean, fat-free, hard, straight, dust-free and dry.

Pevalit

PU-KLEBER

One component
polyurethane adhesive

TECHNICAL PARAMETERS

-**Temperatures of use:** from +5°C - +25°C.

-**Resistant to temperatures:** -40°C - +110°C.

-**Drying(23°C/50%):** approx. 10 min.

-**Drying(23°C/50%):** approx. 60 min for 3 cm thickness.

-**Thermal permeability:** 0.03 W/mK

-**Pressure resistance (10%(DIN 53421):** 3.3 N/cm²

-**Purpose and Water absorption (DIN53429):** 70gr/(m²h24)

-**Material loss:** max. 3%.

-**Cleaning:** with PU-Reiniger

-**Packaging:** in tubes 750ml; (12 tubes/packet).

-**Best before:** In the original packaging 12 months, in a warehouse without moisture, jashtë ndikimit të frost.

