



# Pevalit

## G220

### NATUR FINISH

Fine Filler



## APPLICATION

- Patinizing plaster based on limestone and cement.
- For patination of rough layers of limestone, cement, plaster, concrete, plasterboard.
- In interior spaces, as a finishing layer with a thickness of 1-5 mm.
- The prepared surface for applying the patina measure should be dry, hard, dust free or coated with tension fluid.
- It is thrown by hand or by machine.

Layer Thickness	Consumption	Surface covered with 20 kg PEVALIT - G200 Natur Finish
1 mm	approx. 1 kg/m <sup>2</sup>	approx. 20 m <sup>2</sup>
2 mm	approx. 2 kg/m <sup>2</sup>	approx. 10 m <sup>2</sup>
3 mm	approx. 3 kg/m <sup>2</sup>	approx. 6.5 m <sup>2</sup>

**Granulation:** from 0-0.1 mm.

**Layer thickness:** from 1 mm to 5 mm.

**Density of raw dry mass:** about 1250 kg/m<sup>3</sup>

**Vapor permeability coefficient:** about 25

**Norm:** EN 998-1/Copy: 2006

**Compressive strength (after 28 days):** CS I,

**Purpose and water absorption:** GP, W0.

**Operating temperatures:** +5°C - +30°C.

**Mixing with water:** With about 8.5 l/20kg.

**Material color:** White.

**Packaging:** 20 kg.

**Shelf life:** 12 months in original packaging, in a moisture-free warehouse.