



Pevalit A600 R

Decorative Plaster







APPLICATION

- -White mineral decorative plastic plaster.
- -As a final layer for decorating surfaces in indoor and outdoor environments.
- -Sprayed by hand or by machine.
- -Produced in several sizes of stone grains and structures.
- -According to the work method, we can achieve the needed structures (circular, with lines, full, etc.).
- -Before use of the decorative plaster, reinforcing liquid should be used on the surface.

Stone Size	Consumption	Surface Covered with 25kg PEVALIT - A600 R	
grain 1 mm	approx. 2 kg/m²	approx. 13 m²	
grain 1.5 mm	approx. 2.5 kg/m²	approx. 10 m²	
grain 2 mm	approx. 3 kg/m²	approx. 8 m²	
grain 3 mm	approx. 4 kg/m²	approx. 6 m²	

-Dry mass density: 1400-1700 kg/m³

-Steam permeability coefficient: ca.23

-Certified: EN ETAG 004 ETA -11/0340

-Work temperatures: +5°C - +30°C.

-Mixing with water: with approximately 8 I/25kg.

-Material color: White.

-Packaging: 25 kg.

-Best before: In the original packaging 12 months,

in a warehouse without moisture.