

# PEVALIT P3W g&m



## Flexible Aandsive for Granite and Marble APPLICATION

- Used for aandsion of tiles from granite and natural marble, porcelain tiles, mosaic stone, glass, ceramics, etc.
- Aandsion of tiles in the system tile on tile, or flooring with a heating system.
- Aandsion of tiles on swimming pools.
- Before aandsion on layers of wood, PVC or metal binding liquid must be used.
- Good features for usage on nonporous and smooth layers.
- Has high durability against high temperatures, frost and moisture.
- Certified in C2TE-S1 class, by norm EN 12004, Rap.No. P 920/05-410-6.

## TECHNICAL PARAMETERS

Toothed Shovel Dimensions	Spending	Surface covered with 25kg PEVALIT - P3 W g&m
6x6x6 mm	approx. 2.1kg/m <sup>2</sup>	approx. 11.6m <sup>2</sup>
8x8x8 mm	approx. 2.8kg/m <sup>2</sup>	approx. 8.8m <sup>2</sup>
10x10x10 mm	approx. 3.6kg/m <sup>2</sup>	approx. 7m <sup>2</sup>

- Working time in container:** Up to 4 hours after mixing.
- Working time:** Up to 30 minutes.
- Work temperatures:** +5°C - +30°C
- Resistant to temperatures:** -30°C - +100°C
- Norm:** C2FE, based on EN 12004.
- Walking on tiles:** After 24 hours. Measurements are based on temp. around 22°C.
- Walking on tiles with weight:** After 4 days.
- On layers of plaster:** PEVALIT-Tiefgrund LF is used.
- Mixing with water:** approximately 4 min., with around 24 % water / 25kg.
- Packaging:** 25 kg.
- Material color:** White.
- Best before:** In the original packaging 12 months, in a warehouse without moisture.