

PEVALIT G1



Gypsum Plaster

APPLICATION

- Plaster on gypsum base.
- For plastering of walls and ceilings, in indoor spaces.
- Sprayed by hand or by machine.
- Layer thickness between 1 and 3 cm.
- Before use in places of smooth and gasbeton concrete, binding liquid needs to be used.

TECHNICAL PARAMETERS

Layer Thickness	Spending	Surface Covered with 25kg PEVALIT - G1
10 mm	approx. 15kg/m ²	approx. 1.7m ²
15 mm	approx. 19kg/m ²	approx. 1.3m ²
20 mm	approx. 25kg/m ²	approx. 1.0m ²

- Sanding: From 0-1.5 mm.
- Working time in container: approximately 1 hour after mixing.
- Layer thickness: between 1 and 3 cm.
- Dry mass density: 1900 kg/1m³
- Steam permeability coefficient: ca.23.
- Norm: MKC EN 13279-1:2006.
- Pressure durability (after 28 days): CS I, ca. 0.9 N/mm².
- Purpose and Water absorption: GP, W0.
- Temperature conductivity:<0,75 W/mK.
- Reaction to fire: A1.
- Work temperatures: +5°C - +30°C.
- Mixing with water: with approximately 7.5 l/25kg.
- Material color: Grey.
- Packaging: 25 kg.
- Best before: In the original packaging 12 months, in a warehouse without moisture.