

# PEVALIT P1 extra



## Tile Adhesive

### APPLICATION

- Is distinguished with a greater time frame for working and corrections, up to 30 minutes.
- Përdoret për ngjitjen e pllakave të qeramikës, me dimensione and pesha më të mëdha.
- Në sipërfaqe të mureve apo dyshemeve në ambiente të brendshme.
- Certified for C1T class, According to norm EN 12004, Rap.No. P 920/05-410-4.

### TECHNICAL PARAMETERS

Dimenzioni i lopatës së dhëmbëzuar	Harxhimi	Sipërfaqja e mbuluar me 25kg PEVALIT-P100
4x4x4 mm	afërs. 1.8 kg/m <sup>2</sup>	afërs. 14 m <sup>2</sup>
6x6x6 mm	afërs. 2.7 kg/m <sup>2</sup>	afërs. 9 m <sup>2</sup>
8x8x8 mm	afërs. 3.6 kg/m <sup>2</sup>	afërs. 7 m <sup>2</sup>

- Working time in container:** Up to 6 hours after mixing.
- Working time:** Up to 10 minutes.
- Work temperatures:** +5°C - +30°C
- Resistant to temperatures:** -10°C - +50°C
- Norm:** C1, based on MKC (EN 12004).
- Walking on tiles:** After 24 hours.
- Walking on tiles with weight:** After 5 days.
- On layers of plaster:** PEVALIT-Tiefgrund LF is used.
- Mixing with water:** approximately 4 min., with around 24 % water / 25kg.
- Packaging:** 25 kg.
- Material color:** White.
- Best before:** In the original packaging 12 months, in a warehouse without moisture.