

# PEVALIT P2-S1



## Flexible Tile Adhesive

### APPLICATION

- For surfaces of outdoor and indoor environments, for example terraces, balconies, facades, etc.
- Tile adhesive over layers of flooring with central heating system.
- Used for porcelain tile adhesive, artificial granite, concrete tiles, stone, ceramics, etc.
- Extruded polyurethane (Styrodur) adhesive, in thermal insulation facades.
- Has good durability against high temperatures, frost and moisture.
- For use on walls and flooring.
- Used to repair damaged surfaces, with thickness up to 8 mm.
- Certified in C2TE class, according to norm EN 12004, Rap.No. P 920/05-410-5.

### TECHNICAL PARAMETERS

| Toothed Shovel Dimensions | Spending                     | Surface covered with 25kg PEVALIT - P2 S1 |
|---------------------------|------------------------------|---|
| 4x4x4 mm                  | approx. 1.5kg/m <sup>2</sup> | approx. 16m <sup>2</sup>                  |
| 6x6x6 mm                  | approx. 2.3kg/m <sup>2</sup> | approx. 11m <sup>2</sup>                  |
| 8x8x8 mm                  | approx. 3.1kg/m <sup>2</sup> | approx. 8m <sup>2</sup>                   |
| 10x10x10 mm               | approx. 3.9kg/m <sup>2</sup> | approx. 6.4m <sup>2</sup>                 |

- Working time in container:** Up to 6 hours after mixing.
- Working time:** Up to 10 minutes.
- Work temperatures:** +5°C - +30°C
- Resistant to temperatures:** -20°C - +80°C
- Norm:** C2TE-S1, based on EN 12004.
- Walking on tiles:** After 12-16 hours. Measurements are based on temp. around 22 °C.
- Walking on tiles with weight:** After 4 days.
- On layers of plaster:** PEVALIT-Tiefgrund LF is used.
- Mixing with water:** approximately 4 min., with around 24 % water / 25kg.
- Packaging:** 25 kg.
- Material color:** Grey.
- Best before:** In the original packaging 12 months, in a warehouse without moisture.