

Pevalit


Aquastop

AB 30R

2C Waterproofing mass

APPLICATION

- Two-component measure for elastic waterproofing of waterproofing.
- Thickness up to 3 mm.
- Based on cement (comp. A) and resin (comp. B).
- For concrete or porous cement mortar walls, horizontal or vertical.
- In external and internal environments.
- For swimming pools, underground facilities, water tanks, terraces, balconies, bathrooms, etc.
- High elasticity and good adhesion even on smooth surfaces.
- Surfaces must be clean, dry, hard, dust-free and grease-free.
- It is applied with a brush or roller, in two or three layers.
- The interval between layers is 4-6 hours.



Thickness of the layer	Consumption	Area covered by 20 kg (comp. A) and 8 kg (comp. B) PEVALIT-Aquastop AB30 R
min 2.0mm	approx. 2.5 kg/m ²	approx. 8.0 m ²
min 2.5mm	approx. 3.1 kg/m ²	approx. 6.5 m ²
min 3.0mm	approx. 3.7 kg/m ²	approx. 5.4 m ²
min 5.0mm	approx. 6.2 kg/m ²	approx. 3.3 m ²

Shelf life: up to 1 hour after mixing.

Operating temperatures: +5°C - +30°C.

Resistant to temperatures: -20°C - +80°C.

Standard: based on EN 14891:2012.

Interval between layers: 4-6 hours.

Exposure to water: After 4 days.

Packaging: 20 + 8 kg. / 5 +2 kg.

Material color: gray.

Shelf life: 12 months in original packaging, in a moisture-free warehouse.

