




Pevalit

A500 R

Decorative Plaster

APPLICATION

- White mineral decorative plaster.
- As a final layer for decorating surfaces in indoor and outdoor environments.
- Sprayed by hand or by machine.
- Produced in several sizes of stone grains and structures.
- According to the work method, we can achieve the needed structures (circular, with lines, full, etc.).
- Before use of the decorative plaster, reinforcing liquid should be used on the surface.



Stone Size	Consumption	Surface Covered with 25kg PEVALIT - A500 R
grain 1 mm	approx. 2 kg/m ²	approx. 13 m ²
grain 1.5 mm	approx. 2.5 kg/m ²	approx. 10 m ²
grain 2 mm	approx. 3 kg/m ²	approx. 8 m ²
grain 3 mm	approx. 4 kg/m ²	approx. 6 m ²

- Dry mass density:** 1400-1700 kg/m³
- Steam permeability coefficient:** ca.23
- Norm:** MKC EN 998-1/Kop: 2006.
- Pressure durability (after 28 days):** CS II, ca. 1.4 N/mm².
- Water absorption:** W0.
- Temperature conductivity:** ≤0,50 W/mK
- Reaction to fire:** A1.
- Work temperatures:** +5°C - +30°C.
- Mixing with water:** with approximately 8 l/25kg.
- Material color:** White.
- Packaging:** 25 kg.
- Best before:** In the original packaging 12 months, in a warehouse without moisture.