



Structural decorative plaster based on silicone









## **APPLICATION**

- -Decorative plaster based on Silicone with protection against algae and moss.
- -As a final layer for decorating surfaces in outdoor environments.
- -Sprayed by hand or by machine.
- -Produced in several sizes of stone grains and structures.
- -According to the work method, we can achieve the needed structures (circular, with lines, full, etc.).
- -Before use of the decorative plaster, reinforcing liquid PEVALIT Kuartzgrunt should be used on the surface.

Stone Size	Consumption	Surface Covered with 25kg PEVALIT-BUNSTEINPUTZ	
grain 0.5 mm	approx. 1.1 kg/m²	 approx. 22.5 m²	
grain 1 mm	approx. 2 kg/m²	approx. 16.5 m²	
grain 1.5 mm	approx. 2.5 kg/m²	 approx. 10 m²	
grain 2 mm	approx. 3 kg/m²	 approx. 8 m²	
grain 3 mm	approx. 4 kg/m²	 approx. 6 m²	

- -Mass density: approx. 1.8 g/cm<sup>3</sup>
- -Steam permeability coefficient: Class I high, sd-value: ↓ 0,14 m.
- -Purpose and Water absorption: Class III low, w-value  $\downarrow$  0,1 kg/(m<sup>2</sup>h0,5)
- -Fire resistance: Class A2 fireproof according to DIN EN 1350.
- -Work temperatures: +5°C +30°C.
- -Mixing with water: according to conditions max. 2%.
- **-Drying:** according to material thickness 12-24 hours based on temp. approx. 20°C. and 65% air humidity.
- -Cleaning of tools: After finishing work with water.
- -Material color: White.
- -Packaging: 25 kg.
- -Best before: In the original packaging 12 months,

in a warehouse without moisture.